TEST REPORT BEA2023205



Date of report: 2023-06-23 page **1 of 2**

Client: BIOENERGY Point D.O.O.

Address: Francuska St. 6, 11000 Belgrade, SERBIA

Order: Fuel testing according EN*plus*® certification program of wood pellets (version 3.0, August 2015)

Order date: 2023-05-23 Receipt of samples: 2023-06-03

Samples: Wood pellets **Testing period**: 2023-06-03 – 2023-06-22

Sample details: 15kg pellets in plastic bag class A1 marked with the internal sample no. BEA2023205-1 and 15kg pellets in plastic bag class A2 marked with the internal sample no. BEA2023205-2

BEA2023205	· ·		result	result	
parameter EN <i>plus</i> ®	limit values A1	limit values A2	-1 A1 Pellets	-2 A2 Pellets	unit
diameter	6 ± 1, 8 ± 1	6 ± 1, 8 ± 1	6	6	mm (ar)
length $(3,15 \le L \ge 40 \text{ mm})$	$(3,15 \le L \le 40)$	$(3,15 \le L \le 40)$	17,8 ± 5,6	14,9 ± 7,2	mm (ar)
length $(40 \le L \le 45 \text{ mm})$	≤1	≤ 1	0,0	0,1	%in mass (ar)
length (> 45 mm)	0	0	0	0	piece(s)
moisture content	≤ 10,0	≤ 10,0	7,6	4,4	%in mass (ar)
ash content	≤ 0,7	≤ 1,2	0,7	1,2	%in mass (db)
mechanical durability	≥ 98,0	≥ 97,5	98,6	98,2	%in mass (ar)
bulk density	$600 \le BD \le 750$	$600 \le BD \le 750$	610	670	kg/m³ (ar)
fines content (< 3,15 mm), bulk	≤1	≤1	-	-	%in mass (ar)
fines content (< 3,15 mm), bags	≤ 0,5	≤ 0,5	0,2	0,2	%in mass (ar)
net calorific value qP,net	≥ 16,5	≥ 16,5	16,5	17,3	MJ/kg (ar)
net calorific value qP,net	≥ 4,6	≥ 4,6	4,60	4,80	kWh/kg (ar)
net calorific value qP,net	-	-	18,1	18,2	MJ/kg (db)
net calorific value qP,net	-	-	5,03	5,05	kWh/kg (db)
gross calorific value qv,gr	-	-	18,0	18,7	MJ/kg (ar)
gross calorific value qv,gr	-	-	5,01	5,20	kWh/kg (ar)
nitrogen content	≤ 0,3	≤0,5	0,09	0,12	%in mass (db)
sulphur content	≤ 0,04	≤ 0,04	0,010	0,010	%in mass (db)
chlorine content	≤ 0,02	≤ 0,02	<0,005	<0,005	%in mass (db)
arsenic	≤1	≤ 1	<0,5	<0,5	mg/kg (db)
cadmium	≤ 0,5	≤ 0,5	<0,1	<0,1	mg/kg (db)
chromium	≤ 10	≤ 10	<1	<1	mg/kg (db)
copper	≤ 10	≤ 10	1,1	1,3	mg/kg (db)
lead	≤ 10	≤ 10	<0,5	<0,5	mg/kg (db)
mercury	≤ 0,1	≤ 0,1	<0,075	<0,075	mg/kg (db)
nickel	≤ 10	≤ 10	<1	<1	mg/kg (db)
zinc	≤ 100	≤ 100	< 5	< 5	mg/kg (db)
shrinking temperature SST	-	-	940	910	°C
deformation temperature DT	≥ 1200	≥ 1100	1460	1470	°C
hemisphere tem perature HT	-	-	>1550	>1550	°C
flow temperature FT	-	-	>1550	>1550	°C


db... dry basis, ar... as received

The test results apply only to the samples investigated. As a rule, they are not the only criteria for assessing the raw material or product in question and its suitability for a specific purpose of application. Test Reports may only be made available to third parties, either free of charge or against payment, if the full wording is given and if the author is expressly named. Unless otherwise indicated, at client's request neither the measurement uncertainty was stated, nor were decision rules agreed. The General Terms and Conditions of BEA Institut für Bioenergie GmbH shall apply as amended.



director in charge







TEST REPORT BEA2023205



Date of report: 2023-06-23 page **2 of 2**

Client: BIOENERGY Point D.O.O.

Address: Francuska St. 6, 11000 Belgrade, SERBIA

Order: Fuel testing according EN*plus*® certification program of wood pellets (version 3.0, August 2015)

Order date: 2023-05-23 Receipt of samples: 2023-06-03

Samples: Wood pellets **Testing period**: 2023-06-03 – 2023-06-22

Sample details: 15kg pellets in plastic bag class A1 marked with the internal sample no. BEA2023205-1 and 15kg pellets in plastic bag class A2 marked with the internal sample no. BEA2023205-2

testing methods standard

sample preparation	ISO 14780:2020
diameter and length	ISO 17829:2015
moisture content	ISO 18134-2:2017
ash content	ISO 18122:2015, performed with proximate analyzer
mechanical durability	ISO 17831-1:2015
fines content < 3,15 mm	ISO 18846:2016
net calorific value /gross calorific value	ISO 18125:2017
bulk density	ISO 17828:2015
carbon, hydrogen, nitrogen content	ISO 16948:2015
chlorine, sulphur content	ISO 16994:2016, quantification according to ISO 10304-1:200

chlorine, sulphur content ISO 16994:2016, quantification according to ISO 10304-1:2007 minor elements ISO 16968:2015, quantification according to ISO 17294-2:2016 ash melting behaviour ISO 21404:2020, ash preparation at 815°C, oxidizing atmosphere

remarks

none

The test results apply only to the samples investigated. As a rule, they are not the only criteria for assessing the raw material or product in question and its suitability for a specific purpose of application. Test Reports may only be made available to third parties, either free of charge or against payment, if the full wording is given and if the author is expressly named. Unless otherwise indicated, at client's request neither the measurement uncertainty was stated, nor were decision rules agreed. The General Terms and Conditions of BEA Institut für Bioenergie GmbH shall apply as amended.



director in charge

DI (FH) Magdalena Wojcik



